



TECHNOLOGY MAKES LIFE BETTER

安徽省蚌埠市高新区兴中路 985 号  
日月科技园

电话: 86-552-3827158

传真: 86-552-3822922

安徽艾约塔硅油有限公司

**IOTA CORPORATION LTD.**

Sunmoon industry park, 985 Xingzhong Road,  
Bengbu, China 233000

Tel: 86-552-3827158

Fax: 86-552-3822922

## TDS of Automotive plating liquid IOTA 9970

### Product advantages

The IOTA 9970 product forms a silicon dioxide film after crystallization. The main body of the product is a special polysiloxane, which is different from the popular silicone-based coating products on the market. It has high hardness, good transparency, oxidation resistance, anti-ultraviolet, high adhesion, good water transfer, and has a brightening effect on car paint (especially for black cars). The product has excellent durability.

### Matters needing attention

Choose dry weather as far as possible.

After the construction of the vehicle, if the water is tested, please wipe the residual water beads after the test.

Wash the car after 24 hours a day.

It's better not to see water within 24 hours after construction. If it rains, try not to go out. If it is necessary, clean the surface water after go out.

This product has a certain chemical smell. Please do not directly face the bottle mouth and wear disposable gloves during construction.

### Product indicators

Solid content	40%	Solvent	mineral oil
Hardness(Chinese pencil)	5H	Transparency(visible light)	> 90%
Adhesion (grid method)	0	Water contact angle	110°

ADD: Sunmoon industry park, 985 Xingzhong Road, Bengbu, China 233000

Tel: 86-552-3827158; Fax: 86-552-3822922 Website: [www.polysilazane.cn](http://www.polysilazane.cn)



TECHNOLOGY MAKES LIFE BETTER

安徽省蚌埠市高新区兴中路 985 号  
日月科技园

电话: 86-552-3827158

传真: 86-552-3822922

安徽艾约塔硅油有限公司

**IOTA CORPORATION LTD.**

Sunmoon industry park, 985 Xingzhong Road,  
Bengbu, China 233000

Tel: 86-552-3827158

Fax: 86-552-3822922

---

### **Operation steps**

New cars do not need to be polished. If there are scratches, please polish them first.

The vehicle is degreased and cleaned to ensure the dry surface of the body.

Take the crystal plating solution and pour it on the eyeglass cloth or professional sponge, and start to wipe on the surface of the car. It is suggested to use a cross wipe, that is, a horizontal wipe, a vertical wipe.

After finishing the wiping, use dry towel to start from the initial position of the wiping for leveling. In order to facilitate the construction, partial construction is recommended. If first do the front car cover, wipe the crystal solution after 1 minute with a dry towel, followed by the door, roof, tail construction.

After observing the flatness of car paint coating surface, the car shall be placed in a clean place for 2 hours and the construction shall be completed.

For details, please contact,

**IOTA CORPORATION LTD.**

Add: Sunmoon industry park, 985 Xingzhong Road, Bengbu, China 233000

Whatsapp/Wechat: 0086-18055207372

QQ: 3374697933

Email: [sales05@siliconeoil.net](mailto:sales05@siliconeoil.net)

Website: [www.polysilazane.cn](http://www.polysilazane.cn)

ADD: Sunmoon industry park, 985 Xingzhong Road, Bengbu, China 233000

Tel: 86-552-3827158; Fax: 86-552-3822922 Website: [www.polysilazane.cn](http://www.polysilazane.cn)